




PCT/GB2204/000628

INVESTOR IN PEOPLE

**PRIORITY
DOCUMENT**
SUBMITTED OR TRANSMITTED IN
COMPLIANCE WITH RULE 17.1(a) OR (b)

The Patent Office
Concept House
Cardiff Road
Newport
South Wales
NP10 8QQ




I, the undersigned, being an officer duly authorised in accordance with Section 74(1) and (4) of the Deregulation & Contracting Out Act 1994, to sign and issue certificates on behalf of the Comptroller-General, hereby certify that annexed hereto is a true copy of the documents as originally filed in connection with the patent application identified therein.

In accordance with the Patents (Companies Re-registration) Rules 1982, if a company named in this certificate and any accompanying documents has re-registered under the Companies Act 1980 with the same name as that with which it was registered immediately before re-registration save for the substitution as, or inclusion as, the last part of the name of the words "public limited company" or their equivalents in Welsh, references to the name of the company in this certificate and any accompanying documents shall be treated as references to the name with which it is so re-registered.

In accordance with the rules, the words "public limited company" may be replaced by p.l.c., plc, P.L.C. or PLC.

Re-registration under the Companies Act does not constitute a new legal entity but merely subjects the company to certain additional company law rules.



BEST AVAILABLE COPY


Signed *[Signature]*

Dated 12 March 2004

Executive Agency of the Department of Trade and Industry

Patents Form 1/77

Patents Act 1977
(Rule 16)



14MAY03 EB07219-1 D02B13
P01/7700 0.00-0311071.5

177

Request for grant of a patent

(See the notes on the back of this form. You can also get an explanatory leaflet from the Patent Office to help you fill in this form)

The Patent Office

Cardiff Road
Newport
South Wales
NP10 8QQ

1.	Your Reference	P58374L		
2.	Patent Application number (The Patent Office will fill in this part):	14 MAY 2003 0311071.5		
3.	Full name, address and postcode of the or each applicant (underline all surnames)	TRANSMIX GROUP LTD The Spinney Heath Road Oxshott KT22 0NN		
	Patents ADP Number (if you know it)			
	If the applicant is a corporate body, give the country/state of its incorporation	GB		
4.	Title of the invention	Remediation of Recycled Glass Waste		
5.	Name of your agent (if you have one)	FRY HEATH & SPENCE LLP		
	"Address for service" in the United Kingdom to which all correspondence should be sent (including the postcode)	The Gables Massetts Road Horley Surrey RH6 7DQ United Kingdom		
	Patents ADP Number (if you know it)	05880273001		
6.	If you are declaring priority from one or more earlier patent applications, give the country and the date of filing of the or each of these earlier applications and (if you know it) the or each application number.	Country	Priority application number (if you know it)	Date of filing (day / month / year)
7.	If this application is divided or otherwise derived from an earlier UK application, give the number and the filing date of the earlier application.	Number of earlier application	Date of filing (day / month / year)	
8.	Is a statement of inventorship and of right to grant of a patent required in support of this request? (Answer 'Yes' if:			
	<ul style="list-style-type: none"> a) any applicant named in part 3 is not an inventor; or b) there is an inventor who is not named as an applicant; or c) any named applicant is a corporate body 			
	(See note (d))			

8630568001

8457554001

yes

Patents Form 1/77

0068849 14 May 03 03:23

Patents Form 1/77

9. Enter the number of sheets for any of the following items you are filing with this form. Do not count copies of the same document.

Continuation sheets of this form

Description 8 ✓
Claim(s) 4 ✓
Abstract 1 ✓
Drawing(s)

CP

10. If you are also filing any of the following, state how many against each item.

Priority documents

Translations of priority documents

Statement of inventorship and right to grant of a patent (Patents Form 7/77)

Request for preliminary examination and search (Patents form 9/77)

Request for substantive examination (Patents form 10/77)

Any other documents (please specify)

11.

I/We request the grant of a patent on the basis of this application.

Signature

Date

Graham James Spence

14 May 2003

12. Name and daytime telephone number of person to contact in the United Kingdom

Graham James LOCK - 01293 776880

Warning

After an application for a patent has been filed, the Comptroller of the Patent Office will consider whether publication or communication of the invention should be prohibited or restricted under Section 22 of the Patents Act 1977. You will be informed if it is necessary to prohibit or restrict your invention in this way. Furthermore, if you live in the United Kingdom, Section 23 of the Patents Act 1977 stops you filing or applying for a patent abroad without first getting written permission from the Patent Office unless an application has been filed at least 6 weeks beforehand in the United Kingdom for a patent for the same invention and either no direction prohibiting publication or communication has been given, or any such direction has been revoked.

Notes

- a) If you need help to fill in this form or you have any questions, please contact the Patent Office on 0645 500505.
- b) Write your answers in capital letters using black ink or you may type them.
- c) If there is not enough space for all the relevant details on any part of this form, please continue on a separate sheet of paper and write "see continuation sheet" in the relevant part(s). Any continuation sheet should be attached to this form.
- d) If you have answered 'Yes' Patents Form 7/77 will need to be filed.
- e) Once you have filled in the form you must remember to sign and date it.
- f) For details of the fee and ways to pay please contact the Patent Office.

Remediation of Recycled Glass Waste

The present invention relates to a flowing screed, for example an anhydrite or alpha-hemihydrate calcium sulphate based flowing floor screed, a cementitious flowing floor screed or a blended cementitious flowing floor screed comprising recycled waste glass sand for the construction of floating, unbonded and bonded screeds. In addition the invention relates to a method for the production of screeds and a method of the remediation of recycled glass waste via the production of any of the above flowing screed types in either bagged format or through delivery to site in bulk.

Within the context of this specification the word "comprises" is taken to mean "includes, among other things". It is not intended to be construed as "consists of only".

A flowing screed is one which can be pumped or poured and comprises a mixture of cement/s, aggregate/ sand and water; calcium sulphate aggregate/ sand and water applied to a eg concrete slab, insulation board or over underfloor heating etc to give a smooth surface finish. Known screeds of this type are ISOCRETE GYVLON TM supplied by Isocrete, LAFARGE GYVLON and AGILIA SCREED supplied by Lafarge, RMC READY-SCREED SUPAFLO supplied by RMC and TARMAC TRUFLOW supplied by Tarmac.

An ever increasing volume of glass waste is resulting in considerable pressure on available land fill space. In view of this, considerable pressure is being exerted to clean up environmental problems associated with the disposal of glass and one process that has been developed to reduce this pressure is a process involving the recycling of waste glass. In this recycling process the waste glass is generally subjected to crushing, washing, grading and sieving to provide a glass sand.

The process however suffers from the disadvantage that the residue glass sand must then be disposed of. At present this is achieved by incorporation into tarmac/ asphalt and roadfill sub-base materials. Clearly, other methods of disposal are desirable.

Therefore, a need exists for a process for the remediation of recycled glass waste to produce a product which is environmentally stable. In addition there is a need for a new product comprising recycled glass waste which is environmentally stable.

The present invention addresses or reduces at least one of the problems set out above.

It has now been found that screed production is one possible method of remediation and encapsulation of the waste glass material within an inorganic matrix resulting in an non-contaminating stable product. Advantageously, the process eliminates the need for landfill disposal of the waste glass and reduces the need for mined or quarried natural materials to be used.

Consequently, in a first aspect the present invention provides a screed comprising recycled glass waste.

Preferably an embodiment of a screed according to the invention comprises a recycled glass waste sand residue. Preferably, an embodiment of the screed comprises 10% to 80% by weight of the recycled glass waste sand residue. More preferably, an embodiment of the screed comprises 20% to 70% by weight of the recycled glass waste sand residue. This provides the advantage that the glass being of a lower specific gravity than conventional sand floats more easily in the flowing floor screed suspension than conventional sands and or aggregates.

Preferably an embodiment of a screed according to the invention comprises recycled glass waste combined with a powder binder or slurry preferably comprising at least one of Calcium Sulphate, Portland Cement, High Alumina Cement, Calcium Sulpho-Aluminate Cement, Silica Fume, Limestone Powder, Pulverised Fuel Ash or a combination of two or more thereof. Preferably an embodiment of the screed comprises recycled glass waste combined with 10% to 90% by weight of a powder binder or slurry preferably comprising at least one of Calcium Sulphate, Portland Cement, High Alumina Cement, Calcium Sulpho-Aluminate Cement, Silica Fume, Limestone Powder, Pulverised Fuel Ash or a combination of two or more thereof.

Preferably an embodiment of the screed comprises recycled glass waste combined with 30% to 80% by weight of a powder binder or slurry preferably comprising at least one of Calcium Sulphate, Portland Cement, High Alumina Cement, Calcium Sulpho-Aluminate Cement, Silica Fume, Limestone Powder, Pulverised Fuel Ash or a combination of two or more thereof.

Preferably the calcium sulphate is selected from at least one of alpha hemihydrate, beta hemihydrate, anhydrite or a combination of two or more thereof.

Preferably the cement is selected from at least one of Portland Cement, High Alumina Cement, Calcium Sulpho-Aluminate Cement or a combination of two or more thereof.

Preferably, an embodiment of a screed according to the present invention comprises a mixture of High Alumina Cement and Portland Cement. Preferably this embodiment of the screed comprises from about 10% to about 90% high alumina cement and from about 1% to about 20% Portland cement. More preferably this embodiment of the screed comprises from about 20% to about 80% high alumina cement and from about 5% to about 15% Portland cement.

Preferably, an alternative embodiment of a screed according to the present invention comprises a mixture of Calcium Sulpho-Aluminate Cement and Portland Cement. Preferably this embodiment of the screed comprises from about 10% to about 90% Calcium Sulpho-Aluminate and from about 1% to about 20% Portland cement. More preferably this embodiment of the screed comprises from about 20% to about 80% Calcium Sulpho-Aluminate and from about 5% to about 15% Portland cement.

Preferably, an embodiment of a screed according to the invention additionally comprises calcium sulphate. Preferably, this embodiment of the screed comprises from about 5% to about 50% alpha-hemihydrate plaster, beta-hemihydrate plaster and/or anhydrite. More preferably, this embodiment of the screed comprises about 40% alpha-hemihydrate plaster and/or anhydrite.

Preferably an embodiment of a screed according to the present invention comprises a limestone powder filler. More preferably, this embodiment of the screed comprises about 10% to about 40% limestone powder filler.

Preferably an alternative embodiment of a screed according to the present invention comprises a pulverised fuel ash powder filler. More preferably, this embodiment of the screed comprises about 10% to about 35% pulverised fuel ash powder filler.

Preferably an alternative embodiment of a screed according to the present invention comprises a silica fume powder filler. More preferably, this embodiment of the screed comprises about 5% to about 20% silica fume powder filler.

Preferably, an embodiment of a screed according to the invention comprises a retarder to retard the cement hydration or calcium sulphate set time thereby extending the pot-life of the flowing screed. Preferably the retarder comprises at least one of citric acid, tartaric acid, boric acid, sodium gluconate, Rochelle salt, tri-sodium citrate, sodium tri-polyphosphate or a combination of two or more thereof. Preferably, an embodiment of the screed comprises 0.025% to 2.0% by weight of the retarder. More preferably, an embodiment of the screed comprises 0.05% to 1% by weight of the retarder. More preferably, an embodiment of the screed comprises 0.2% to 0.8% by weight of the retarder.

Preferably, an embodiment of a screed according to the present invention comprises an accelerator to promote hydration of the cement or calcium sulphate materials. Preferably the accelerator comprises at least one of lithium carbonate, sodium carbonate, aluminium sulphate, phosphate salts or a combination of two or more thereof. Preferably, an embodiment of the screed comprises 0.025% to 2.0% by weight of the accelerator. More preferably, an embodiment of the screed comprises 0.025% to 1% by weight of the accelerator. More preferably, an embodiment of the screed comprises 0.2% to 0.8% by weight of the accelerator. This provides the advantage that the cements and/or calcium sulphates will hydrate or set rapidly once retardation has ceased.

Preferably, an embodiment of a screed according to the present invention comprises a plasticiser. Preferably the plasticiser comprises at least one of melamines, ligno-sulphonates, caseins or a combination of two or more thereof which enhance the flow characteristics of the flowing floor screed without having to add excess water. Thus, reduced amounts of water can be used and/or excess water can be avoided. Preferably an embodiment of the screed comprises 0.02% to 2.00% by weight of the plasticiser. More preferably, an embodiment of the screed comprises 0.1% to 0.8% by weight of the plasticiser. More preferably, an embodiment of the screed comprises 0.2% to 0.5% by weight of the plasticiser.

Preferably, an embodiment of a screed according to the present invention comprises a liquid and/or powdered organic polymers. Preferably the liquid and/or powdered polymers comprise at least one of organic polymers, co-polymers, ter-polymers or a combination of two or more thereof which improve surface abrasion, bond strength to substrates and aggregate and or sand suspension. Preferably, an embodiment of the screed comprises 1% to 6% by weight of the liquid and/or powdered organic polymer. More preferably, an embodiment of the screed comprises 2% to 4% by weight of the liquid and/or powdered organic polymer. More preferably, an embodiment of the screed comprises 3% by weight of the liquid and/or powdered organic polymer.

In a second aspect the invention provides a method for production of a screed according to a first aspect of the invention which comprises the steps of mixing the components in the required amounts.

Preferably, an embodiment of the method includes the steps of keeping the powder binder or slurry components separate from the glass sand until the screed is required and then mixing the components on site directly before applying the flowing screed to a floor substrate or of first combining the components and mixing them either on site or off site in a bulk ready-mix truck or ready-mix pump truck before applying the flowing screed to a floor substrate surface.

In a third aspect the invention provides a method for remediation of recycled glass waste which comprises the steps of crushing, washing, sieving and grading of waste.

glass to produce a sand residue as a component in the production of a flowing screed.

Additional features and advantages of the present invention are described in, and will be apparent from, the description of the presently preferred embodiments which are set out below.

For the purposes of clarity and a concise description features are described herein as part of the same or separate embodiments, however it will be appreciated that the scope of the invention may include embodiments having combinations of all or some of the features described.

Example 1

In a preferred embodiment a flowing screed according to the invention comprises 10% to 80% by weight of recycled glass waste sand residue, 20% to 90% by weight alpha hemihydrate plaster, 0.025% to 2% by weight by weight retarder and 0.02% to 2.00% by weight of plasticiser.

Example 2

In an alternative preferred embodiment a screed according to the invention comprises 10% to 80% by weight of recycled glass waste sand, 20% to 90% by weight anhydrite and 0.025% to 2.00% by weight accelerator and 0.02% to 2.00% by weight of plasticiser.

Example 3

In an alternative preferred embodiment a screed according to the invention comprises 10% to 80% by weight of recycled glass waste sand, 20% to 90% by weight Portland cement.

Example 4

In an alternative preferred embodiment a screed according to the invention comprises 10% to 80% by weight of recycled glass waste sand, 10% to 80% by weight high alumina cement, 10% to 35% by weight limestone powder filler, 1% to

20% by weight Portland cement, 5% to 15% by weight beta-hemihydrate plaster and/ or 5% to 15% by weight anhydrite, 0.025% to 2% by weight accelerator, 0.025% to 2% by weight retarder, and 0.020% to 2% by weight plasticiser.

Example 5

In an alternative preferred embodiment a screed according to the invention comprises 10% to 80% by weight of recycled glass waste sand, 10% to 80% by weight high alumina cement, 10% to 35% by weight limestone powder filler, 1% to 20% by weight Portland cement, 5% to 15% by weight beta-hemihydrate plaster and/ or 5% to 15% by weight anhydrite, 0.025% to 2% by weight accelerator, 0.025% to 2% by weight retarder, 0.020% to 2% by weight plasticiser, and 1% to 5% by weight liquid and/ or powdered organic polymer.

Example 6

In an alternative preferred embodiment a screed according to the invention comprises 10% to 80% by weight of recycled glass waste sand, 10% to 80% by weight calcium sulph-aluminate cement, 10% to 35% by weight limestone powder filler, 1% to 20% by weight Portland cement, 5% to 15% by weight beta-hemihydrate plaster and/ or 5% to 15% by weight anhydrite, 0.025% to 2% by weight accelerator, 0.025% to 2% by weight retarder, 0.020% to 1% by weight plasticiser, and 1% to 5% by weight liquid and/ or powdered organic polymer

Example 7

In an alternative preferred embodiment a screed according to the invention comprises 10% to 80% by weight of recycled glass waste sand, 10% to 80% by weight high alumina cement, 10% to 35% by weight limestone powder filler, 1% to 20% by weight Portland cement, 5% to 15% by weight beta-hemihydrate plaster and/ or 5% to 15% by weight anhydrite, 5% to 20% silica fume, 0.025% to 2% by weight accelerator, 0.025% to 2% by weight retarder, 0.020% to 2% by weight plasticiser, and 1% to 5% by weight liquid and/ or powdered organic polymer.

Example 8

In an alternative preferred embodiment a screed according to the invention comprises 10% to 80% by weight of recycled glass waste sand, 10% to 80% by

P58374L

8

weight calcium sulph-aluminate cement, 10% to 35% by weight limestone powder filler, 1% to 20% by weight Portland cement, 5% to 15% by weight beta-hemihydrate plaster and/ or 5% to 15% by weight anhydrite, 5% to 20% silica fume, 0.025% to 2% by weight accelerator, 0.025% to 2% by weight retarder, 0.020% to 1% by weight plasticiser, and 1% to 5% by weight liquid and/ or powdered organic polymer

It should be understood that various changes and modifications to the presently preferred embodiments described herein will be apparent to those skilled in the art.

Such changes and modifications can be made without departing from the spirit and scope of the present invention and without diminishing its attendant advantages. It is therefore intended that such changes and modifications are covered by the appended claims.

Claims

1. A screed comprising recycled glass waste or a recycled glass waste sand residue.
2. A screed according to claim 1 which comprises 10% to 80% by weight of the recycled glass waste sand residue.
3. A screed according to claim 1 or 2 which comprises at least one of calcium sulphate, Portland Cement, High Alumina Cement, Calcium Sulpho-Aluminate Cement, limestone powder, silica fume, pulverised fuel ash or a combination of two or more thereof.
4. A screed according to claim 3 which comprises 10% to 90% by weight of at least one of Calcium Sulphate, cement, plaster or a combination of two or more thereof.
5. A screed according to claim 4 wherein the calcium sulphate is selected from at least one of alpha hemihydrate plaster, beta hemihydrate plaster, anhydrite or a combination of two or more thereof.
6. A screed according to claim 4 wherein the cement is selected from at least one of Portland Cement, High Alumina Cement, Calcium Sulpho-Aluminate Cement, silica fume, pulverised fuel ash or a combination of two or more thereof.
7. A screed according to claim 6 which comprises a mixture of High Alumina Cement and Portland Cement.
8. A screed according to claim 7 which comprises from about 10% to about 80% high alumina cement and from about 1% to about 20% Portland cement.
9. A screed according to claim 6 which comprises a mixture of Calcium Sulpho-Aluminate Cement and Portland Cement.

10. A screed according to claim 9 which comprises from about 10% to about 80% Calcium Sulpho-Aluminate and from about 1% to about 20% Portland cement.
11. A screed according to any preceding claim which additionally comprises beta-hemihydrate plaster and/or anhydrite.
12. A screed according to claim 11 which comprises from about 5% to about 50% beta hemihydrate plaster and/or anhydrite.
13. A screed according to any preceding claim which comprises a limestone powder filler.
14. A screed according to claim 13 which comprises about 10% to about 35% limestone powder filler.
15. A screed according to any preceding claim which comprises a pulverised fuel ash powder filler.
16. A screed according to claim 15 which comprises about 10% to about 35% pulverised fuel ash powder filler.
17. A screed according to claim 15 which comprises about 5% to about 20% silica fume powder filler.
18. A screed according to any preceding claim which comprises a retarder for retarding the cement hydration thereby extending the pot-life of the flowing screed.
19. A screed according to claim 18 wherein the retarder comprises at least one of citric acid, tartaric acid, boric acid, sodium gluconate, Rochelle salt, tri-sodium citrate, sodium tri-polyphosphate or a combination of two or more thereof.

20. A screed according to claim 18 or 19 wherein the screed comprises 0.025% to 2.0% by weight of the retarder.
21. A screed according to any preceding claim which comprises an accelerator for promoting hydration of the cement or calcium sulphate materials.
22. A screed according to claim 21 wherein the accelerator comprises at least one of lithium carbonate, sodium carbonate, aluminium sulphate, phosphate salts or a combination of two or more thereof.
23. A screed according to claim 22 wherein the screed comprises 0.025% to 2.0% by weight of the accelerator.
24. A screed according to any preceding claim which comprises a plasticiser.
25. A screed according to claim 24 wherein the plasticiser comprises at least one of melamines, ligno-sulphonates, caseins or a combination of two or more thereof which enhance the flow characteristics of the flowing floor screed without having to add excess water.
26. A screed according to claim 24 or 25 wherein the screed comprises 0.02% to 2.00% by weight of the plasticiser.
27. A screed according to any preceding claim which comprises a liquid and/or powdered organic polymer.
28. A screed according to claim 27 wherein the liquid and/or powdered polymers comprise at least one of organic polymers, co-polymers, ter-polymers or a combination of two or more thereof which improve surface abrasion, bond strength to substrates and aggregate and or sand suspension.
29. A screed according to claim 27 or 28 wherein the screed comprises 1% to 6% by weight of the liquid and/or powdered organic polymer.

30. A method for production of a screed according to any one of claims 1 to 29 which comprises the steps of mixing the components in the required amounts.
31. A method according to claim 30 which includes the steps of keeping the components separate until the screed is required and then mixing the components on site directly before applying the flowing screed to a floor substrate or of first combining the components and mixing them either on site or off site in a bulk ready-mix truck before applying the flowing screed to a floor substrate surface.
32. A method for remediation of recycled glass waste which comprises at least one of the steps of crushing, washing, sieving and grading of waste glass to produce a sand residue as a component in the production of a flowing screed or a combination of two or more thereof.
33. A screed as described herein with reference to the accompanying examples.

P58374L

13

Abstract**Remediation of Sewage Waste Incinerator Residue**

A screed for applying to eg a concrete slab, etc to give a smooth surface finish comprises recycled glass waste sand residue. In a preferred embodiment the screed comprises 10% to 80% by weight of the sand residue coated with incinerated sewage waste. A method for production of a screed is described as well as a method for remediation of recycled glass waste.

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☐ FADED TEXT OR DRAWING
- ☐ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☐ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.